


**NEU- We Make A Material Difference**



## **Neuthane N8511-1H**

**A Blend of Aromatic, Polyester TPUs with good clarity.**

Hardness (Shore A)	65
Tensile (psi) Tensile Strength @100%	2600 329
Elongation at break (%)	809

For best processing, moisture content of resin is to be  $\leq 0.01\%$ . Contact NEU for further information.